

To Whom it may concern,

This material is currently produced at our "Ortona" facility (FDOT mine #05-045) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

## 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	98	%	
	#30 (.6mm)	72	%	
	#50 (.3mm)	33	%	
	#100 (.15mm)	3	%	
	#200 (75µm)	0.1	%	

Sincerely,

## Mario Cardenas

Quality Control Manager E.R. Jahna Ind, Inc. Office: 352-394-7455 Cell: 863-528-2335

Cell: 863-528-2335 Fax: 352-394-8730