



07/03/2024

1004-Well Point Sand

Procedure	Sieve/Test	Average	Unit	Well Point
	#4 (4.75mm)	99.9	%	95-100
	#8 (2.36mm)	97.8	%	85-100
	#16 (1.18mm)	87.0	%	64-97
	#30 (.6mm)	52.3	%	19-70
	#50 (.3mm)	12.6	%	3-35
	#100 (.15mm)	2.1	%	0-7
	#200 (75µm)	0.12	%	
ASTM C-136	FM	2.484		2.600-2.900

Name/Title

David Clements / Mine manager