




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 07/19/2024 - 07/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	15	100.0	0.00	95-100	
#8 (2.36mm)	15	99.9	0.05	85-100	
#16 (1.18mm)	15	95.6	0.72	65-97	
#30 (.6mm)	15	69.4	2.78	25-75	
#50 (.3mm)	15	37.9	3.32	5-40	
#100 (.15mm)	15	4.4	1.37	0-7	
#200 (75µm)	15	0.3	0.19		
Pan	15	0.0	0.00		
FM	15	1.93	0.056	1.82-2.18\2	1.8-2.2
Grad Loss	15	0.030	0.0503		
Total Moisture	15	4.4	0.92	1-5	1-5
D10 (ES)	15	0.1686	0.00444		
D50	15	0.39	0.025		
D60	15	0.49	0.028		
Cc	15	0.80	0.044		
Cu	15	2.90	0.174		



Query

Query Selections

Date Created 07/26/2024

Date Range 07/19/2024 - 07/26/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping