



Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 07/19/2024 - 07/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100	0.0	97-100	
#8 (2.36mm)	3	100	0.0	97-100	
#16 (1.18mm)	3	100	0.0	95-100	
#30 (.6mm)	3	98	0.0	85-100	
#50 (.3mm)	3	90	1.2	35-90	
#100 (.15mm)	3	10	0.0	3-35	
#200 (75µm)	3	0.2	0.23		
Pan	3	0.0	0.00		
FM	3	1.03	0.012	0.9-1.4	1.2
Grad Loss	3	0.028	0.0491		
Total Moisture	3	5.2	0.51	0-5.5	0-6
D10 (ES)	3	0.1501	0.00006		
D50	3	0.21	0.000		
D60	3	0.23	0.000		
Cc	3	0.92	0.000		
Cu	3	1.54	0.012		



Query

Query Selections

Date Created 07/26/2024

Date Range 07/19/2024 - 07/26/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping