




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 07/19/2024 - 07/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	2	100.0	0.00		95-100
#8 (2.36mm)	2	99.8	0.07		85-100
#16 (1.18mm)	2	92.8	1.48		65-97
#30 (.6mm)	2	47.9	5.37		25-70
#50 (.3mm)	2	5.6	3.39		5-35
#100 (.15mm)	2	0.3	0.14		0-7
#200 (75µm)	2	0.08	0.078		0-4
Pan	2	0.00	0.000		
FM	2	2.54	0.106	2.6	2.6-2.99
Total Moisture	2	3.4	0.42		
D10 (ES)	2	0.3232	0.01916		
D50	2	0.62	0.049		
D60	2	0.72	0.042		
Cu	2	2.22	0.014		



Query

Query Selections
Date Created 07/26/2024
Date Range 07/19/2024 - 07/26/2024
Plant Green Bay Mine (FDOT Pit #16-608)
Sample Type Shipping