




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 07/19/2024 - 07/26/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100.0	0.00	95-100	
#8 (2.36mm)	3	99.9	0.00	85-100	
#16 (1.18mm)	3	96.4	0.53	65-99	
#30 (.6mm)	3	54.1	2.31	25-70	
#50 (.3mm)	3	13.5	1.68	5-35	
#100 (.15mm)	3	0.7	0.25	0-7	
#200 (75µm)	3	0.0	0.00		
Pan	3	0.0	0.00		
FM	3	2.36	0.035		
Total Moisture	3	3.6	0.15		
D10 (ES)	3	0.25	0.020		
D50	3	0.56	0.021		
D60	3	0.66	0.021		
D15/D85	3	0.31	0.010		
Cc	3	0.96	0.030		
Cu	3	2.64	0.172		



Query

Query Selections
Date Created 07/26/2024
Date Range 07/19/2024 - 07/26/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping