




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	11	100.0	0.00	95-100	
#8 (2.36mm)	11	99.9	0.05	85-100	
#16 (1.18mm)	11	96.2	0.94	65-97	
#30 (.6mm)	11	71.9	3.59	25-75	
#50 (.3mm)	11	38.8	2.92	5-40	
#100 (.15mm)	11	3.2	0.91	0-7	
#200 (75µm)	11	0.6	0.45		
Pan	11	0.0	0.00		
FM	11	1.90	0.074	1.82-2.18\2	1.8-2.2
Grad Loss	11	0.042	0.0608		
Total Moisture	11	4.1	0.86	1-5	1-5
D10 (ES)	11	0.1713	0.00397		
D50	11	0.38	0.024		
D60	11	0.47	0.032		
Cc	11	0.80	0.042		
Cu	11	2.74	0.143		



Query

Query Selections

Date Created 10/18/2024

Date Range 10/11/2024 - 10/18/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping