




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	100	0.0	95-100	
#30 (.6mm)	7	96	0.5	85-100	
#50 (.3mm)	7	82	4.0	35-90	
#100 (.15mm)	7	7	2.3	3-35	
#200 (75µm)	7	1.0	0.41		
Pan	7	0.0	0.00		
FM	7	1.15	0.024	0.9-1.4	1.2
Grad Loss	7	0.024	0.0343		
Total Moisture	7	4.2	0.38	0-5.5	0-6
D10 (ES)	7	0.1523	0.00859		
D50	7	0.22	0.005		
D60	7	0.24	0.008		
Cc	7	0.92	0.026		
Cu	7	1.62	0.146		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Green Bay Mine (FDOT Pit #16-608)
Sample Type Shipping