




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1004-Well Point Sand  
**Specification** FLDOT Silica Sand  
**Period** 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100.0	0.00		95-100
#8 (2.36mm)	7	99.8	0.05		85-100
#16 (1.18mm)	7	92.9	0.63		65-97
#30 (.6mm)	7	41.4	1.84		25-70
#50 (.3mm)	7	<b>3.1</b>	0.80		5-35
#100 (.15mm)	7	0.5	0.13		0-7
#200 (75µm)	7	0.03	0.021		0-4
Pan	7	0.00	0.000		
FM	7	2.62	0.021	2.6	2.6-2.99
Total Moisture	7	2.5	0.45		
D10 (ES)	7	0.3400	0.00314		
D50	7	0.67	0.016		
D60	7	0.77	0.011		
Cu	7	2.25	0.051		



**Query**

Query Selections

Date Created 10/18/2024

Date Range 10/11/2024 - 10/18/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping