



10/03/2024

To Whom it may concern,

This material is currently produced at our "Haines City" facility (FDOT mine #16-024) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	99	%	
	#50 (.3mm)	77	%	
	#100 (.15mm)	14	%	
	#200 (75µm)	0.2	%	
ASTM C-136	FM	1.10		
ASTM C-566	Total Moisture	3.1	%	0.0-7.0
	D10 (ES)	0.12	mm	
	D50	0.22	mm	
	D60	0.25	mm	
	Cc	1.04		
	Cu	2.01		

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-557-0342
Fax: 352-394-8730

Name/Title

David Clements / Mine manager