




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100.0	0.00	95-100	95-100
#8 (2.36mm)	5	99.9	0.11	85-100	85-100
#16 (1.18mm)	5	96.3	1.15	65-98	65-100
#30 (.6mm)	5	70.5	3.68	25-75	≥25
#50 (.3mm)	5	37.5	3.43	5-44	5-45
#100 (.15mm)	5	8.1	1.60	0-10	0-10
#200 (75µm)	5	0.1	0.00	0-4	0-4
Pan	5	0.0	0.00		
FM	5	1.87	0.076	1.8-2.2\2	
Total Moisture	5	3.1	0.07	0-5	0-6
D10 (ES)	5	0.15	0.005		
D50	5	0.39	0.026		
D60	5	0.48	0.033		
Cc	5	0.84	0.078		
Cu	5	3.08	0.209		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Haines City Mine (FDOT Pit #16-024)
Sample Type Shipping