




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.0	90-100	
#30 (.6mm)	5	98	1.1	65-100	
#50 (.3mm)	5	80	6.7	35-90	
#100 (.15mm)	5	21	5.2	0-40	
#200 (75µm)	5	0.2	0.00		
Pan	5	0.0	0.00		
FM	5	1.02	0.128		
Total Moisture	5	3.2	0.19	0-6\3	0-7
D10 (ES)	5	0.11	0.013		
D50	5	0.21	0.017		
D60	5	0.24	0.020		
Cc	5	1.10	0.058		
Cu	5	2.23	0.099		



Query

Query Selections

Date Created 10/18/2024

Date Range 10/11/2024 - 10/18/2024

Plant Haines City Mine (FDOT Pit #16-024)

Sample Type Shipping