




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100	0.0	97-100	
#8 (2.36mm)	8	100	0.0	97-100	
#16 (1.18mm)	8	100	0.4	95-100	
#30 (.6mm)	8	95	2.9	85-100	
#50 (.3mm)	8	58	8.2	35-90	
#100 (.15mm)	8	8	3.4	0-35	
#200 (75µm)	8	0.2	0.07		
Pan	8	0.0	0.00		
FM	8	1.39	0.123	1.05-1.45\1.2	
Total Moisture	8	3.1	1.48	0-5	0-6
D10 (ES)	8	0.1508	0.01386		
D50	8	0.27	0.027		
D60	8	0.31	0.035		
Cc	8	0.89	0.063		
Cu	8	2.08	0.149		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping