




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.9	0.00	85-100	
#16 (1.18mm)	6	95.4	0.60	65-99	
#30 (.6mm)	6	48.8	2.71	25-70	
#50 (.3mm)	6	13.3	3.14	5-35	
#100 (.15mm)	6	1.1	0.54	0-7	
#200 (75µm)	6	0.0	0.00		
Pan	6	0.0	0.00		
FM	6	2.42	0.049		
Total Moisture	5	3.4	0.16		
D10 (ES)	6	0.26	0.033		
D50	6	0.61	0.024		
D60	6	0.70	0.021		
D15/D85	6	0.30	0.027		
Cc	6	0.96	0.051		
Cu	6	2.79	0.349		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping