




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FDOT Concrete Silica Sand Code F01
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	9	100.0	0.00		95-100
#8 (2.36mm)	9	99.8	0.05		85-100
#16 (1.18mm)	9	95.0	0.69	67-96	65-97
#30 (.6mm)	9	46.5	2.21	27-68	25-70
#50 (.3mm)	9	10.5	1.72		5-35
#100 (.15mm)	9	0.8	0.58		0-7
#200 (75µm)	9	0.0	0.00		
Pan	9	0.0	0.00		
FM	9	2.47	0.026	2.22-2.57/2.4	2.2-2.6
Grad Loss	9	0.000	0.0000		
Total Moisture	9	3.2	0.25		
D10 (ES)	9	0.29	0.021		
D50	9	0.63	0.019		
D60	9	0.72	0.017		
Cc	9	0.92	0.072		
Cu	9	2.53	0.266		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping