




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1008-Mason Sand
Specification Mason Sand
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	100-100	
#8 (2.36mm)	5	100	0.0	100-100	
#16 (1.18mm)	5	98	0.8	97-100	
#30 (.6mm)	5	81	1.4	80-100	
#50 (.3mm)	5	48	4.7	43-85	
#100 (.15mm)	5	5	1.1	0-25	
#200 (75µm)	5	0.1	0.00		
Pan	5	0.0	0.00		
FM	5	1.68	0.052		
Grad Loss	5	0.000	0.0000		
Total Moisture	5	4.2	0.18	0-5	0-6
D10 (ES)	5	0.16	0.005		
D50	5	0.31	0.025		
D60	5	0.38	0.029		
D15/D85	5	0.25	0.013		
Cu	5	2.33	0.139		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping