




Basic Quality Statistical Summary Report

Plant 1210-Liberty Sand Mine
Product 117-GDOT 10NS Concrete Sand
Specification GADOT 10NS
Period 10/11/2024 - 10/18/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
3/8" (9.5mm)	7	100.00	0.000		
#4 (4.75mm)	8	99.63	0.160		95-100
#8 (2.36mm)	8	94.52	2.240		
#16 (1.18mm)	8	75.30	4.147		45-95
#30 (.6mm)	8	46.87	6.551		
#50 (.3mm)	8	20.86	5.735		5-30
#100 (.15mm)	8	3.90	2.272		0-10
#200 (75µm)	8	0.22	0.211		0-3
Pan	8	0.00	0.000		
FM	8	2.59	0.146	2.4-2.85\2.65	
Grad Loss	8	0.014	0.0403		
Total Moisture	8	4.5	0.85	0-5\4	0-6
D10 (ES)	8	0.20	0.028		
D50	8	0.64	0.092		
D15/D85	1	0.18			
Cu	8	4.18	0.507		



Query

Query Selections
Date Created 10/18/2024
Date Range 10/11/2024 - 10/18/2024
Plant Liberty Sand Mine
Sample Type Shipping