



11/05/2024

### 1004-Well Point Sand

| Procedure  | Sieve/Test   | Average | Unit | Well Point Sand |
|------------|--------------|---------|------|-----------------|
|            | #4 (4.75mm)  | 100     | %    |                 |
|            | #8 (2.36mm)  | 100     | %    |                 |
|            | #16 (1.18mm) | 93      | %    |                 |
|            | #30 (.6mm)   | 40      | %    |                 |
|            | #50 (.3mm)   | 8       | %    |                 |
|            | #100 (.15mm) | 0       | %    |                 |
|            | #200 (75µm)  | 0.0     | %    |                 |
| ASTM C-136 | FM           | 2.59    |      |                 |

**Name/Title**

David Clements / Mine manager