



11/05/2024

To Whom it may concern,

This material is currently produced at Liberty Sand Mine. This material is shipped and produced utilizing an approved quality control plan. The fine aggregate "**Mason Sand**" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	97	%	
	#16 (1.18mm)	91	%	
	#30 (.6mm)	78	%	
	#50 (.3mm)	49	%	
	#100 (.15mm)	11	%	
	#200 (75µm)	0.3	%	
ASTM C-136	FM	1.73		

Sincerely,

Mario Cardenas

Quality Control Manager

E.R. Jahna Ind, Inc.

Office: 863-424-0730

Cell: 863-557-0342

Fax: 352-394-8730

Name/Title

David Clements / Mine manager