




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (.6mm)	4	99	0.5	85-100	
#50 (.3mm)	4	96	1.0	35-90	
#100 (.15mm)	4	16	0.6	0-35	
#200 (75µm)	4	0.8	0.12		
Pan	4	0.0	0.00		
FM	4	0.891	0.0128	1.05-1.45\1.2	
Total Moisture	4	7.518	1.5430	0-5	0-6
D10 (ES)	4	0.12	0.005		
D50	4	0.20	0.000		
D60	4	0.22	0.000		
Cc	4	1.13	0.014		
Cu	4	1.89	0.033		



Query

Query Selections
Date Created 11/20/2024
Date Range 11/13/2024 - 11/20/2024
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping