




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	99	0.8	95-100	
#30 (.6mm)	6	94	4.7	85-100	
#50 (.3mm)	6	59	10.2	35-90	
#100 (.15mm)	6	11	3.2	0-35	
#200 (75µm)	6	0.3	0.10		
Pan	6	0.0	0.00		
FM	6	1.38	0.179	1.05-1.45	1.2
Total Moisture	6	3.3	0.86	0-5	0-6
D10 (ES)	6	0.1415	0.01726		
D50	6	0.27	0.038		
D60	6	0.31	0.050		
Cc	6	0.92	0.081		
Cu	6	2.22	0.262		



**Query**

Query Selections  
Date Created 11/20/2024  
Date Range 11/13/2024 - 11/20/2024  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping