




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	15	100.0	0.00	95-100	
#8 (2.36mm)	15	99.9	0.05	85-100	
#16 (1.18mm)	15	96.5	0.49	65-97	
#30 (.6mm)	15	72.2	2.44	25-75	
#50 (.3mm)	15	37.6	2.61	5-40	
#100 (.15mm)	15	3.3	1.07	0-7	
#200 (75µm)	15	0.2	0.17		
Pan	15	0.0	0.00		
FM	15	1.90	0.043	1.82-2.18\2	1.8-2.2
Grad Loss	15	0.018	0.0342		
Total Moisture	15	3.5	0.62	1-5	1-5
D10 (ES)	15	0.1718	0.00382		
D50	15	0.38	0.015		
D60	15	0.47	0.019		
Cc	15	0.82	0.047		
Cu	15	2.74	0.116		



Query

Query Selections

Date Created 11/20/2024

Date Range 11/13/2024 - 11/20/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping