



Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100	0.0	97-100	
#8 (2.36mm)	7	100	0.0	97-100	
#16 (1.18mm)	7	100	0.0	95-100	
#30 (.6mm)	7	96	1.3	85-100	
#50 (.3mm)	7	84	1.9	35-90	
#100 (.15mm)	7	8	1.1	3-35	
#200 (75µm)	7	0.5	0.53		
Pan	7	0.0	0.00		
FM	7	1.12	0.026	0.9-1.4	1.2
Grad Loss	7	0.025	0.0423		
Total Moisture	7	2.8	0.89	0-5.5	0-6
D10 (ES)	7	0.1526	0.00141		
D50	7	0.22	0.000		
D60	7	0.24	0.004		
Cc	7	0.91	0.005		
Cu	7	1.58	0.020		



Query

Query Selections

Date Created 11/20/2024

Date Range 11/13/2024 - 11/20/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping