




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1004-Well Point Sand  
**Specification** FLDOT Silica Sand  
**Period** 11/13/2024 - 11/20/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	7	100.0	0.00		95-100
#8 (2.36mm)	7	99.8	0.08		85-100
#16 (1.18mm)	7	90.4	0.69		65-97
#30 (.6mm)	7	42.7	3.44		25-70
#50 (.3mm)	7	1.7	1.40		5-35
#100 (.15mm)	7	0.1	0.05		0-7
#200 (75µm)	7	0.03	0.029		0-4
Pan	7	0.00	0.000		
FM	7	2.65	0.046	2.6	2.6-2.99
Total Moisture	7	2.6	0.54		
D10 (ES)	7	0.3454	0.00996		
D50	7	0.66	0.029		
D60	7	0.76	0.022		
Cu	7	2.22	0.037		



**Query**

Query Selections

Date Created 11/20/2024

Date Range 11/13/2024 - 11/20/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping