



12/01/2024

To Whom it may concern,

This material is currently produced at our "Green Bay" facility (FDOT mine #16-608) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "**Mason Sand**" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	96	%	
	#50 (.3mm)	85	%	
	#100 (.15mm)	8	%	
	#200 (75µm)	0.4	%	

Sincerely,

Mario Cardenas

Quality Control Manager

E.R. Jahna Ind, Inc.

Office: 352-394-7455

Cell: 863-557-0342

Fax: 352-394-8730



12/01/2024

Name/Title Mario Cardenas / Quality Control Manager