



12/01/2024

To Whom it may concern,

This material is currently produced at our "Haines City" facility (FDOT mine #16-024) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.9	%	85-100
	#16 (1.18mm)	96.5	%	65-100
	#30 (.6mm)	71.9	%	≥25
	#50 (.3mm)	38.1	%	5-45
	#100 (.15mm)	7.2	%	0-10
	#200 (75µm)	0.1	%	0-4

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-557-0342
Fax: 352-394-8730

Name/Title Mario Cardenas / Quality Control Manager