




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	99.8	0.29		95-100
#8 (2.36mm)	5	98.4	0.96		85-100
#16 (1.18mm)	5	90.5	2.77	67-98	65-99
#30 (.6mm)	5	71.8	12.16	27-79	25-80
#50 (.3mm)	5	37.4	5.81	7-38	5-40
#100 (.15mm)	5	4.4	1.89	0-6	0-7
#200 (75µm)	5	0.1	0.09		0-4
Pan	5	0.0	0.00		
FM	5	1.976	0.2030	1.87-2.18\2	1.85-2.2
Total Moisture	4	3.402	0.9915		
D10 (ES)	5	0.17	0.007		
D50	5	0.39	0.054		
D60	5	0.49	0.077		
Cc	5	0.82	0.090		
Cu	5	2.88	0.352		



Query

Query Selections
Date Created 12/16/2024
Date Range 12/09/2024 - 12/16/2024
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping