




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FLDOT Silica Sand
Period 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100	0.0	95-100	95-100
#8 (2.36mm)	10	100	0.0	85-100	85-100
#16 (1.18mm)	10	94	1.4	67-96	65-97
#30 (.6mm)	10	60	6.7	27-68	25-70
#50 (.3mm)	10	20	5.2	7-33	5-35
#100 (.15mm)	10	1	0.6	0-6	0-7
#200 (75µm)	10	0	0.0	0-4	0-4
Pan	10	0	0.0		
FM	10	2.25	0.133	2.3	2.1-2.5
-#200 (75um)	1	0.08			
Grad Loss	10	0.025	0.0481		
Wash Loss (#200/75um)	1	0.06			
Total Moisture	10	3.4	0.35		
D10 (ES)	10	0.2167	0.03325		
D50	10	0.51	0.061		
D60	10	0.60	0.069		
Cc	10	1.00	0.060		
Cu	10	2.80	0.250		



Query

Query Selections

Date Created 12/16/2024

Date Range 12/09/2024 - 12/16/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping