



# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.0	95-100	
#30 (.6mm)	5	97	1.8	85-100	
#50 (.3mm)	5	84	4.7	35-90	
#100 (.15mm)	5	9	0.7	3-35	
#200 (75µm)	5	0.0	0.04		
Pan	5	0.0	0.00		
FM	5	1.10	0.059	0.9-1.4	1.2
Grad Loss	5	-0.019	0.0416		
Total Moisture	5	3.3	0.88	0-5.5	0-6
D10 (ES)	5	0.1513	0.00088		
D50	5	0.22	0.004		
D60	5	0.24	0.004		
Cc	5	0.91	0.007		
Cu	5	1.59	0.052		



**Query**

Query Selections

Date Created 12/16/2024

Date Range 12/09/2024 - 12/16/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping