




# Basic Quality Statistical Summary Report

**Plant** 1130-Green Bay Mine (FDOT Pit #16-608)  
**Product** 1004-Well Point Sand  
**Specification** FLDOT Silica Sand  
**Period** 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	99.8	0.08		85-100
#16 (1.18mm)	4	91.3	2.27		65-97
#30 (.6mm)	4	38.5	1.81		25-70
#50 (.3mm)	4	<b>2.5</b>	1.98		5-35
#100 (.15mm)	4	0.2	0.26		0-7
#200 (75µm)	4	0.08	0.066		0-4
Pan	4	0.00	0.000		
FM	4	2.68	0.042	2.6	2.55-2.99
Total Moisture	4	3.1	0.24		
D10 (ES)	4	0.3464	0.01090		
D50	4	0.70	0.017		
D60	4	0.79	0.021		
Cu	4	2.28	0.089		



**Query**

Query Selections

Date Created 12/16/2024

Date Range 12/09/2024 - 12/16/2024

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping