



12/05/2024

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.6	%	85-100
	#16 (1.18mm)	93.1	%	65-99
	#30 (.6mm)	65.9	%	25-80
	#50 (.3mm)	25.1	%	5-40
	#100 (.15mm)	1.7	%	0-7
	#200 (75µm)	0.0	%	0-4
AASHTO T-27	FM	2.15		1.85-2.20
AASHTO T-255	Total Moisture	4.1	%	
	D10 (ES)	0.1925	mm	
	D50	0.46	mm	
	D60	0.54	mm	
	Cc	1.02		
	Cu	2.82		

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730

Name/Title

David Clements / Mine manager