




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100	0.0	97-100	
#8 (2.36mm)	10	100	0.0	97-100	
#16 (1.18mm)	10	100	0.0	95-100	
#30 (.6mm)	10	97	1.2	85-100	
#50 (.3mm)	10	64	6.3	35-90	
#100 (.15mm)	10	10	2.4	0-35	
#200 (75µm)	10	0.3	0.09		
Pan	10	0.0	0.00		
FM	10	1.30	0.091	1.05-1.45	1.2
Total Moisture	10	4.1	1.12	0-5	0-6
D10 (ES)	10	0.1451	0.01182		
D50	10	0.25	0.019		
D60	10	0.29	0.028		
Cc	10	0.91	0.062		
Cu	10	2.00	0.142		



**Query**

Query Selections  
Date Created 12/16/2024  
Date Range 12/09/2024 - 12/16/2024  
Plant Independent North Mine (FDOT Pit #11-490)  
Sample Type Shipping