




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1001-FDOT Concrete Silica Sand Code F01
Specification FDOT Concrete Silica Sand Code F01
Period 12/09/2024 - 12/16/2024

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	10	100.0	0.00		95-100
#8 (2.36mm)	10	99.8	0.08		85-100
#16 (1.18mm)	10	94.2	0.97	67-96	65-97
#30 (.6mm)	10	44.2	3.00	27-68	25-70
#50 (.3mm)	10	11.4	2.28		5-35
#100 (.15mm)	10	0.7	0.40		0-7
#200 (75µm)	10	0.0	0.00		
Pan	10	0.0	0.00		
FM	10	2.50	0.041	2.22-2.57/2.4	2.2-2.6
Grad Loss	10	0.000	0.0000		
Total Moisture	10	3.5	0.32		
D10 (ES)	10	0.27	0.027		
D50	10	0.65	0.024		
D60	10	0.74	0.022		
Cc	10	0.98	0.068		
Cu	10	2.74	0.285		



Query

Query Selections
Date Created 12/16/2024
Date Range 12/09/2024 - 12/16/2024
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping