



01/03/2025

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Mason Sand" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	97	%	
	#50 (.3mm)	65	%	
	#100 (.15mm)	11	%	
	#200 (75µm)	0.3	%	
AASHTO T-27	FM	1.27		
AASHTO T-255	Total Moisture	3.7	%	0.0-6.0
	D10 (ES)	0.1406	mm	
	D50	0.25	mm	
	D60	0.28	mm	
	Cc	0.93		
	Cu	2.03		

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 352-394-7455  
Cell: 863-528-2335  
Fax: 352-394-8730

Name/Title

David Clements / Mine manager