




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	5	100	0.0	97-100	
#8 (2.36mm)	5	100	0.0	97-100	
#16 (1.18mm)	5	100	0.0	95-100	
#30 (.6mm)	5	98	1.0	85-100	
#50 (.3mm)	5	71	10.4	35-90	
#100 (.15mm)	5	12	6.1	0-35	
#200 (75µm)	5	0.3	0.10		
Pan	5	0.0	0.00		
FM	5	1.20	0.129	1.05-1.45\1.2	
Total Moisture	5	3.8	0.70	0-5	0-6
D10 (ES)	5	0.1373	0.02381		
D50	5	0.24	0.023		
D60	5	0.27	0.026		
Cc	5	0.96	0.104		
Cu	5	2.00	0.321		



Query

Query Selections
Date Created 01/03/2025
Date Range 12/23/2024 - 01/03/2025
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping