




Basic Quality Statistical Summary Report

Plant 1070-Independent South Mine (FDOT Pit#11-298)
Product 1008-Mason Sand
Specification Mason Sand
Period 12/23/2024 - 01/03/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	1	100		97-100	
#8 (2.36mm)	1	100		97-100	
#16 (1.18mm)	1	100		95-100	
#30 (.6mm)	1	99		85-100	
#50 (.3mm)	1	83		35-90	
#100 (.15mm)	1	11		0-35	
#200 (75µm)	1	0.3			
Pan	1	0.0			
FM	1	1.064		1.05-1.45\1.2	
Total Moisture	1	5.471		0-5	0-6
D10 (ES)	1	0.14			
D50	1	0.22			
D60	1	0.24			
Cc	1	0.98			
Cu	1	1.75			



Query

Query Selections
Date Created 01/03/2025
Date Range 12/23/2024 - 01/03/2025
Plant Independent South Mine (FDOT Pit#11-298)
Sample Type Shipping