



02/04/2025

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-298) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "**Mason Sand**" product number (1008) is a washed and graded product. Each load is accompanied by an individual ticket.

### 1008-Mason Sand

Procedure	Sieve/Test	Average	Unit	Mason Sand
	#4 (4.75mm)	100	%	
	#8 (2.36mm)	100	%	
	#16 (1.18mm)	100	%	
	#30 (.6mm)	98	%	
	#50 (.3mm)	88	%	
	#100 (.15mm)	12	%	
	#200 (75µm)	0.3	%	
ASTM C-136	FM	1.035		
ASTM C-566	Total Moisture	8.048	%	0.000-6.000
	D10 (ES)	0.14	mm	
	D50	0.22	mm	
	D60	0.24	mm	
	Cc	1.00		
	Cu	1.73		

Sincerely,

*Mario Cardenas*

Quality Control Manager  
E.R. Jahna Ind, Inc.  
Office: 863-424-0730 ext.515  
Cell: 863-557-0342

Name/Title

David Clements / Mine manager