



02/04/2025

To Whom it may concern,

This material is currently produced at our "Independent" facility (FDOT mine #11-490) this material is shipped and produced utilizing an approved quality control plan. The fine aggregate "Concrete Sand" product number (1009) is a washed and graded product. Each load is accompanied by an individual ticket.

1009-Concrete Sand

Procedure	Sieve/Test	Average	Unit	Concrete Sand
	#4 (4.75mm)	100.0	%	95-100
	#8 (2.36mm)	99.5	%	85-100
	#16 (1.18mm)	91.5	%	65-99
	#30 (.6mm)	61.4	%	25-80
	#50 (.3mm)	23.1	%	5-40
	#100 (.15mm)	0.9	%	0-7
	#200 (75µm)	0.1	%	0-4
AASHTO T-27	FM	2.24		1.85-2.20
AASHTO T-255	Total Moisture	4.3	%	
	D10 (ES)	0.1992	mm	
	D50	0.49	mm	
	D60	0.58	mm	
	Cc	0.99		
	Cu	2.94		

Sincerely,

Mario Cardenas

Quality Control Manager
E.R. Jahna Ind, Inc.
Office: 352-394-7455
Cell: 863-528-2335
Fax: 352-394-8730

Name/Title

David Clements / Mine manager