




Basic Quality Statistical Summary Report

Plant 1050-Independent North Mine (FDOT Pit #11-490)
Product 1008-Mason Sand
Specification Mason Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100	0.0	97-100	
#8 (2.36mm)	6	100	0.0	97-100	
#16 (1.18mm)	6	100	0.0	95-100	
#30 (.6mm)	6	98	0.5	85-100	
#50 (.3mm)	6	75	4.9	35-90	
#100 (.15mm)	6	17	4.4	0-35	
#200 (75µm)	6	0.2	0.30		
Pan	6	0.0	0.00		
FM	6	1.10	0.093	1.05-1.45\1.2	
Total Moisture	6	4.5	0.99	0-5	0-6
D10 (ES)	6	0.1158	0.01298		
D50	6	0.22	0.012		
D60	6	0.25	0.012		
Cc	6	1.07	0.066		
Cu	6	2.18	0.146		



Query

Query Selections
Date Created 02/21/2025
Date Range 02/14/2025 - 02/21/2025
Plant Independent North Mine (FDOT Pit #11-490)
Sample Type Shipping