




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	14	100.0	0.00	95-100	
#8 (2.36mm)	14	99.9	0.00	85-100	
#16 (1.18mm)	14	95.7	0.67	65-97	
#30 (.6mm)	14	69.7	3.91	25-75	
#50 (.3mm)	14	37.8	4.39	5-40	
#100 (.15mm)	14	2.8	0.50	0-7	
#200 (75µm)	14	0.2	0.15		
Pan	14	0.0	0.00		
FM	14	1.94	0.088	1.82-2.18\2	1.8-2.2
Grad Loss	14	0.040	0.0557		
Total Moisture	14	3.4	0.49	1-5	1-5
D10 (ES)	14	0.1734	0.00424		
D50	14	0.39	0.036		
D60	14	0.49	0.040		
Cc	14	0.80	0.041		
Cu	14	2.81	0.174		



Query

Query Selections

Date Created 02/21/2025

Date Range 02/14/2025 - 02/21/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping