




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100	0.0	97-100	
#8 (2.36mm)	4	100	0.0	97-100	
#16 (1.18mm)	4	100	0.0	95-100	
#30 (.6mm)	4	93	2.5	85-100	
#50 (.3mm)	4	84	1.3	35-90	
#100 (.15mm)	4	8	2.4	3-35	
#200 (75µm)	4	1.1	1.00		
Pan	4	0.0	0.00		
FM	4	1.16	0.043	0.9-1.4	1.2
Grad Loss	4	0.116	0.1126		
Total Moisture	4	3.4	0.26	0-5.5	0-6
D10 (ES)	4	0.1506	0.00638		
D50	4	0.22	0.000		
D60	4	0.24	0.000		
Cc	4	0.92	0.024		
Cu	4	1.60	0.052		



Query

Query Selections

Date Created 02/21/2025

Date Range 02/14/2025 - 02/21/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping