




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	3	100.0	0.00		95-100
#8 (2.36mm)	3	99.9	0.00		85-100
#16 (1.18mm)	3	93.1	1.17		65-97
#30 (.6mm)	3	46.5	4.82		25-70
#50 (.3mm)	3	2.4	0.58		5-35
#100 (.15mm)	3	0.2	0.12		0-7
#200 (75µm)	3	0.02	0.021		0-4
Pan	3	0.00	0.000		
FM	3	2.58	0.046	2.6	2.55-2.99
Total Moisture	3	2.9	0.38		
D10 (ES)	3	0.3383	0.00346		
D50	3	0.63	0.036		
D60	3	0.73	0.036		
Cu	3	2.15	0.095		



Query

Query Selections

Date Created 02/21/2025

Date Range 02/14/2025 - 02/21/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping