




Basic Quality Statistical Summary Report

Plant 1030-Haines City Mine (FDOT Pit #16-024)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100.0	0.00	95-100	95-100
#8 (2.36mm)	8	99.9	0.06	85-100	85-100
#16 (1.18mm)	8	96.5	0.74	65-98	65-100
#30 (.6mm)	8	74.2	3.72	25-75	≥25
#50 (.3mm)	8	44.4	4.15	5-44	5-45
#100 (.15mm)	8	8.4	1.36	0-10	0-10
#200 (75µm)	8	0.2	0.12	0-4	0-4
Pan	8	0.0	0.00		
FM	8	1.77	0.085	1.8-2.2\2	
Total Moisture	8	4.4	1.23	0-5	0-6
D10 (ES)	8	0.16	0.005		
D50	8	0.34	0.033		
D60	8	0.43	0.039		
Cc	8	0.78	0.023		
Cu	8	2.80	0.268		



Query

Query Selections
Date Created 02/21/2025
Date Range 02/14/2025 - 02/21/2025
Plant Haines City Mine (FDOT Pit #16-024)
Sample Type Shipping