




# Basic Quality Statistical Summary Report

**Plant** 1070-Independent South Mine (FDOT Pit#11-298)  
**Product** 1009-Concrete Sand  
**Specification** Concrete Sand  
**Period** 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	4	100.0	0.00		95-100
#8 (2.36mm)	4	98.9	0.13		85-100
#16 (1.18mm)	4	93.2	2.72	67-98	65-99
#30 (.6mm)	4	72.7	12.35	27-79	25-80
#50 (.3mm)	4	<b>48.0</b>	19.44	7-38	5-40
#100 (.15mm)	4	<b>6.8</b>	3.66	0-6	0-7
#200 (75µm)	4	0.2	0.13		0-4
Pan	4	0.0	0.00		
FM	4	<b>1.803</b>	0.3808	1.87-2.18\2	1.85-2.2
Total Moisture	4	4.383	3.2249		
D10 (ES)	4	0.16	0.021		
D50	4	0.35	0.107		
D60	4	0.44	0.143		
Cc	4	0.82	0.106		
Cu	4	2.68	0.613		



**Query**

Query Selections  
Date Created 02/21/2025  
Date Range 02/14/2025 - 02/21/2025  
Plant Independent South Mine (FDOT Pit#11-298)  
Sample Type Shipping