




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 02/14/2025 - 02/21/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.8	0.08	85-100	
#16 (1.18mm)	6	95.4	0.63	65-99	
#30 (.6mm)	6	50.7	1.52	25-70	
#50 (.3mm)	6	11.6	1.81	5-35	
#100 (.15mm)	6	0.7	0.18	0-7	
#200 (75µm)	6	0.0	0.00		
Pan	6	0.0	0.00		
FM	6	2.42	0.016		
Total Moisture	6	3.8	0.08		
D10 (ES)	6	0.27	0.022		
D50	6	0.59	0.016		
D60	6	0.69	0.014		
D15/D85	6	0.32	0.010		
Cc	6	0.92	0.046		
Cu	6	2.54	0.249		



Query

Query Selections
Date Created 02/21/2025
Date Range 02/14/2025 - 02/21/2025
Plant Ortona Sand Company (FDOT Pit # 05-045)
Sample Type Shipping