




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 03/12/2025 - 03/19/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	17	100.0	0.00	95-100	
#8 (2.36mm)	17	99.9	0.02	85-100	
#16 (1.18mm)	17	96.2	0.45	65-97	
#30 (.6mm)	17	71.2	3.34	25-75	
#50 (.3mm)	17	35.6	3.77	5-40	
#100 (.15mm)	17	2.9	0.67	0-7	
#200 (75µm)	17	0.2	0.19		
Pan	17	0.0	0.00		
FM	17	1.94	0.075	1.82-2.18\2	1.8-2.2
Grad Loss	17	0.063	0.0854		
Total Moisture	17	3.5	0.65	1-5	1-5
D10 (ES)	17	0.1748	0.00479		
D50	17	0.40	0.025		
D60	17	0.48	0.031		
Cc	17	0.86	0.063		
Cu	17	2.76	0.128		



Query

Query Selections

Date Created 03/19/2025

Date Range 03/12/2025 - 03/19/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping