




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1008-Mason Sand
Specification Mason Sand
Period 03/12/2025 - 03/19/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	8	100	0.0	97-100	
#8 (2.36mm)	8	100	0.0	97-100	
#16 (1.18mm)	8	100	0.0	95-100	
#30 (.6mm)	8	95	1.5	85-100	
#50 (.3mm)	8	81	6.3	35-90	
#100 (.15mm)	8	9	2.4	3-35	
#200 (75µm)	8	0.4	0.48		
Pan	8	0.0	0.00		
FM	8	1.15	0.065	0.9-1.4	1.2
Grad Loss	8	0.061	0.0960		
Total Moisture	8	3.4	0.19	0-5.5	0-6
D10 (ES)	8	0.1482	0.01081		
D50	8	0.22	0.011		
D60	8	0.25	0.013		
Cc	8	0.94	0.044		
Cu	8	1.67	0.183		



Query

Query Selections

Date Created 03/19/2025

Date Range 03/12/2025 - 03/19/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping