




Basic Quality Statistical Summary Report

Plant 1130-Green Bay Mine (FDOT Pit #16-608)
Product 1004-Well Point Sand
Specification FLDOT Silica Sand
Period 03/12/2025 - 03/19/2025

| Sieve/Test | Tests | Average | St Dev | Target | Specification |
|----------------|-------|---------|---------|--------|---------------|
| #4 (4.75mm) | 8 | 100.0 | 0.00 | | 95-100 |
| #8 (2.36mm) | 8 | 99.8 | 0.05 | | 85-100 |
| #16 (1.18mm) | 8 | 91.6 | 1.08 | | 65-97 |
| #30 (.6mm) | 8 | 44.5 | 2.32 | | 25-70 |
| #50 (.3mm) | 8 | 2.3 | 1.14 | | 5-35 |
| #100 (.15mm) | 8 | 0.2 | 0.18 | | 0-7 |
| #200 (75µm) | 8 | 0.03 | 0.030 | | 0-4 |
| Pan | 8 | 0.00 | 0.000 | | |
| FM | 8 | 2.62 | 0.023 | 2.6 | 2.55-2.99 |
| Total Moisture | 8 | 2.8 | 0.25 | | |
| D10 (ES) | 8 | 0.3402 | 0.00542 | | |
| D50 | 8 | 0.65 | 0.019 | | |
| D60 | 8 | 0.75 | 0.019 | | |
| Cu | 8 | 2.20 | 0.057 | | |



Query

Query Selections

Date Created 03/19/2025

Date Range 03/12/2025 - 03/19/2025

Plant Green Bay Mine (FDOT Pit #16-608)

Sample Type Shipping