




# Basic Quality Statistical Summary Report

**Plant** 1050-Independent North Mine (FDOT Pit #11-490)  
**Product** 1008-Mason Sand  
**Specification** Mason Sand  
**Period** 02/19/2025 - 03/19/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	15	100	0.0	97-100	
#8 (2.36mm)	15	100	0.0	97-100	
#16 (1.18mm)	15	100	1.0	95-100	
#30 (.6mm)	15	97	3.6	85-100	
#50 (.3mm)	15	71	2.1	35-90	
#100 (.15mm)	15	11	2.6	0-35	
#200 (75µm)	15	0.3	0.21		
Pan	15	0.0	0.00		
FM	15	1.22	0.067	1.05-1.45\1.2	
Total Moisture	15	4.4	1.46	0-5	0-6
D10 (ES)	15	0.1392	0.01398		
D50	15	0.24	0.006		
D60	15	0.27	0.006		
Cc	15	0.95	0.069		
Cu	15	1.92	0.181		



**Query**

Query Selections

Date Created 03/19/2025

Date Range 02/19/2025 - 03/19/2025

Plant Independent North Mine (FDOT Pit #11-490)

Sample Type Shipping