




Basic Quality Statistical Summary Report

Plant 2010-Ortona Sand Company (FDOT Pit # 05-045)
Product 1009-Concrete Sand
Specification Concrete Sand
Period 03/12/2025 - 03/19/2025

Sieve/Test	Tests	Average	St Dev	Target	Specification
#4 (4.75mm)	6	100.0	0.00	95-100	
#8 (2.36mm)	6	99.8	0.12	85-100	
#16 (1.18mm)	6	94.0	0.73	65-99	
#30 (.6mm)	6	51.3	4.34	25-70	
#50 (.3mm)	6	15.9	4.90	5-35	
#100 (.15mm)	6	0.8	0.39	0-7	
#200 (75µm)	6	0.0	0.05		
Pan	6	0.0	0.00		
FM	6	2.38	0.096		
Total Moisture	6	3.4	0.78		
D10 (ES)	6	0.24	0.032		
D50	6	0.58	0.044		
D60	6	0.68	0.039		
D15/D85	6	0.28	0.034		
Cc	6	0.96	0.034		
Cu	6	2.90	0.289		



Query

Query Selections

Date Created 03/19/2025

Date Range 03/12/2025 - 03/19/2025

Plant Ortona Sand Company (FDOT Pit # 05-045)

Sample Type Shipping